

Name	Polymer	Grind types						Density g/cc	MFI*	MPT (°C)	Applications			Feature
		<300	<400	<500	<800	<1000	<1200				Masterbatch	Textiles & Carpet backing	Hot Melt Adhesive	
N2100	LDPE			•			•	0.923	2	110	•			Low MFI
N2102	LDPE			•	•		•	0.919	7.5	106	•			Higher mpt
N2103	LDPE			•	•		•	0.924	6.5	111	•			Medium MFI
N2105	LDPE		•	•			•	0.917	21	106	•	•		Good flow (MFI)
N2106	LDPE	•		•			•	0.924	22	108	•	•		Higher mpt
N2140	LDPE		•	•	•		•	0.917	40	106	•	•		Good flow (MFI)
N2170	LDPE	•	•	•	•		•	0.916	70	102	•	•	•	High flow
N2215	LDPE			•		•	•	0.913	150	99	•	•	•	Very high flow
N2220	LDPE			•				0.915	200	102	•	•	•	Very high flow
N2301	LLDPE				•	•	•	0.924	20	123	•	•		Higher mpt & toughness
N2302	LLDPE		•		•	•	•	0.926	50	123	•	•		Higher mpt & toughness
N2303	LLDPE					•	•	0.936	5	125	•	•		Higher mpt & toughness
N2004	POP			•				0.902	30	97		•		Olefin elastomer high flow
N2803	HDPE			•				0.964	8	134	•			High stiffness & mpt
N2805	HDPE			•	•	•		0.954	20	133	•	•		High stiffness & mpt
N4420	PP h						•	0.900	20*	160	•			For use in polymer specific masterbatches
N4450	PP h						•	0.905	47*	160	•			For use in polymer specific masterbatches
N4503	PP co						•	0.905	25*	150	•			For use in polymer specific masterbatches

\* MFI at 2.16/190°C

For more information contact: [europesales@icopolymers.com](mailto:europesales@icopolymers.com) [www.icopolymers.com](http://www.icopolymers.com)

Name	Polymer	Grind types						Density g/cc	MFI*	VA%	MPT (°C)	Applications			Feature
		<300	<400	<500	<800	<1000	<1200					Masterbatch	Textiles & Carpet backing	Hot Melt Adhesive	
N1001	EVA			•	•	•		0.941	0.65	19	84	•			Low MFI, high toughness
N1003	EVA					•		0.939	1.7	18	86	•			Low MFI, high toughness
N1007	EVA	•				•		0.934	7.5	14	88	•			Also available as Ultra fine 125u
N1013	EVA				•			0.949	400	28	70		•	•	High flow and adhesion, low mpt
N1009	EVA			•	•	•	•	0.940	20	20	79	•	•	•	Balanced combination
N1012	EVA			•		•		0.953	25	28	71	•	•	•	High adhesion, low mpt
N1014	EVA			•	•	•		0.956	45	33	59	•	•	•	High adhesion, low mpt
N1015	EVA			•		•	•	0.938	150	19	81	•	•	•	High flow
N1016	EVA	•		•	•	•		0.950	150	28	66	•	•	•	High flow, high adhesion
N6401	PS						•	1.040	3			•			For use in polymer specific masterbatches
N6404	PS						•	1.050	20			•			For use in polymer specific masterbatches
N6502	HIPS						•	1.040	20			•			For use in polymer specific masterbatches
N9501	SAN				•		•	1.070	6			•			For use in polymer specific masterbatches
N9903	PMMA				•		•	1.180	50			•			For use in polymer specific masterbatches
N9901	PC						•	1.200	12			•			For use in polymer specific masterbatches
N9602	PA6	•					•	1.130	NA			•			For use in polymer specific masterbatches
N9201	PET						•	1.270	NA			•			For use in polymer specific masterbatches
N9902	EMA						•	0.940	2.8			•			For use in polymer specific masterbatches
N9301	PBT						•	1.300	52			•			For use in polymer specific masterbatches
N9701	PUR						•	1.230	NA			•			For use in polymer specific masterbatches

\* MFI settings- LDPE and EVA 190°C and 2.16kg, PS&HIPS 200C and 5kg,

For more information contact: [europesales@icopolymers.com](mailto:europesales@icopolymers.com) [www.icopolymers.com](http://www.icopolymers.com)

ICO Polymers does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not on the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. The information transmitted herewith is given in good faith. ICO's products are manufactured to the highest quality standards. Please note, however, that all express and implied warranties are expressly denied, and ICO makes no guarantees with respect to goods manufactured by its customers or others with ICO materials. The suitability for application and the performance of any goods manufactured with materials processed and/or sold by ICO is the sole responsibility of the end user. Product design and parameters of end user's use and manufacturing processes (e.g. design of moulds and moulded products, moulding conditions and quality control, conditions of use in service, etc.) are among the various factors that affect the performance of the final products, and these and other factors are outside of ICO's expertise and area of control.